



A 40-MIL, POLYETHYLENE BLEND PEEL-AND-STICK FLASHING MEMBRANE

MortarFlash™ Non-Asphaltic Flashing

DESCRIPTION

MortarFlash™ Non-Asphaltic Flashing is a 40-mil, polyethylene blend peel-and-stick flashing membrane with applications to:

Masonry | Concrete | Steel | Gypsum | Wood

- Tear resistant
- Will not drool when exposed to UV or heat
- Primer is not required; however, we recommend the use of a termination bar and a bead of sealant under the leading edge of the flashing
- When the use of prefabricated accessories is not feasible, MortarFlash Non-Asphaltic can be used to create inside and outside corners.

AVAILABLE FLASHING COMPONENTS

Recommended for use with MortarFlash Non-Asphaltic MortarNet OR WallDefender

- Mortar dropping collection device
- Available in 3/8", 1", 1-1/2", and 2" thicknesses

Termination Bars

- PVC - 1/8" thick, UV stabilized
- Stainless steel - 16 gauge Type 304
- Stainless steel w/ lip - 16 gauge Type 304

Drip Edge

- Stainless steel - 28 gauge Type 304

Inside/Outside Corners & End Dams

- Synthetic rubber (SR)
- TPO (Thermoplastic Polyolefin)

Metal Drip Edge Corners

- Stainless Steel Pre-formed Outside 90°
- Stainless Steel Adjustable 325° to 22°



Sizes & Packaging					
Thickness	Roll Height	Roll Length	Rolls/Box	SF/Box	Boxes/Pallet
0.040"	9"	75'	4	225	132
	12"		3	225	99
	16"		2	200	52
	18"		2	225	60
	20"		1	125	50
	24"		1	150	50
	36"		1	225	30

TECHNICAL DATA

UV Accelerated Weathering ASTM G154

- Mullen Burst ASTM D751 - 400 psi - 2760 kPa
- More than 90% strength retained after 2000 hours exposure

Heat Resistance

- Short Exposure - 194 F. (90 C)
- Continuous Exposure - 160 F. (71 C)
- Melting Point - 230 F (110 C)

Tensile Strength ASTM D751

- Machine Direction - 230 lbs. - 105 kg.
- Cross Direction - 210 lb. - 95 kg.
- Force Elongation 20%

